



## Product Data Sheet

# Hyspin HVI

High Viscosity Index anti-wear Hydraulic oils

## Description

The Castrol Hyspin™ HVI range of high viscosity index (VI) oils is based on a carefully selected ashless (zinc free) additive system designed to meet and exceed the most exacting performance standards.

## Application

Hyspin HVI oils are intended for severely stressed hydraulic systems requiring a high level of anti-wear performance and fine filtration. In addition, Hyspin HVI exhibits excellent corrosion protection as well as outstanding thermal and oxidative stability. Hyspin HVI has excellent hydrolytic stability and separates rapidly from water contamination. Hyspin HVI contains a shear stable additive system which helps to maintain the viscosity characteristics of the product over a wide temperature range, even during prolonged use, and imparts a very low pour point which enables the product to be used in cold environments. The Hyspin HVI range is fully compatible with elastomer materials commonly used for static and dynamic seals, such as nitrile, silicone and fluorinated (e.g. Viton) polymers.

Applications include:

- Outdoor equipment which are likely to operate over wide temperature ranges, such as machinery subjected to cold start up conditions and high temperature continuous running. Examples include off-highway and marine applications.
- Indoor manufacturing equipment that incorporates control systems requiring minimal viscosity change with temperature. Examples include precision machine tools.

Hyspin HVI is classified as follows:

- DIN 51502 classification – HVLP
- ISO 6743/4 - Hydraulic Oils Type HV

Hyspin HVI (for appropriate viscosity grade) is approved by:

- Parker Hannifin (Denison) HF0, HF1 & HF2
- Eaton E-FDGN-TB002-E

Hyspin HVI grades meet the requirements (for appropriate viscosity grade) of:

- DIN 51524 Part 3
- Cincinnati Lamb (Milacron) P 68-69-70
- US Steel 126 & 127

## Advantages

- High viscosity index and low pour point enables the product to be used over a wide temperature range. Good shear stability means no excessive loss in viscosity due to mechanical shearing.
- Excellent anti-wear performance provides extended wear protection for hydraulic pumps. Reduced down time due to unscheduled maintenance and savings from replacement part costs.
- Excellent water separation and hydrolytic stability means reduced down time through prolonged lubricant life and increased equipment reliability.
- Excellent thermal and oxidative stability provides reliable performance and extended oil life in severe applications. Minimal deposit formation gives a cleaner system and reduced frequency of filter changes.
- Excellent filterability characteristics (including in the presence of water) enables cost savings to be made due to increased filter life.

# Typical Characteristics

Name	Method	Units	HVI 15	HVI 22	HVI 32	HVI 46	HVI 68	HVI 100
ISO Viscosity Grade	-	-	15	22	32	46	68	100
Density @ 15°C / 59°F	ISO 12185 / ASTM D4052	kg/m <sup>3</sup>	840	850	852	859	866	870
Kinematic Viscosity @ 40°C / 104°F	ISO 3104 / ASTM D445	mm <sup>2</sup> /s	15	22	32	46	68	100
Kinematic Viscosity @ 100°C / 212°F	ISO 3104 / ASTM D445	mm <sup>2</sup> /s	3.7	4.7	6.1	7.9	10.8	14.6
Viscosity Index	ISO 2909 / ASTM 2270	-	>140	>140	>140	>140	>140	>140
Pour Point	ISO 3016 / ASTM D97	°C/°F	-45/-49	-51/-60	-51/-60	-45/-49	-45/-49	-42/-
Flash Point - closed cup method	ISO 2719 / ASTM D93	°C/°F	190/ 374	200/ 392	220/ 428	223/ 433	238/460	240/4
Foam Sequence I - tendency / stability	ISO 6247/ ASTM D892	ml/ml	20/0	20/0	20/0	20/0	20/0	20/0
Water Separation @ 54°C / 129°F (40/37/3)	ISO 6614/ ASTM D1401	min	5	10	10	10	10	-
Water Separation @ 82°C / 180°F (40/37/3)	ISO 6614/ ASTM D1401	min	-	-	-	-	-	10
Air Release @ 50°C / 122°F	ISO 9120/ ASTM D3427	min	1	1	2	3	6	12
FZG Gear Scuffing test - A/8.3/90	ISO 14635-1	Failure Load Stage	-	-	12	12	12	12
Rust test - distilled water (24 hrs)	ISO 7210 / ASTM D665A	Rating	Pass	Pass	Pass	Pass	Pass	Pass
Rust test - synthetic seawater (24 hrs)	ISO 7210 / ASTM D665B	Rating	Pass	Pass	Pass	Pass	Pass	Pass
KRL Tapered Roller Bearing Shear Stability Test (20h, 60°C, 5KN, 1450rpm)	CEC L-45-A-99	viscosity loss (%)	2.3	4.0	5.3	7.3	9	11
Oxidation Stability - TOST	ISO 4263-1 / ASTM D943	hours	-	-	>5000	>5000	>5000	-

Subject to usual manufacturing tolerances.

Hyspin HVI  
28 May 2024  
Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, to the extent that it is permissible by law to exclude warranties and representations, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. Refer to the MSDS, available from our website for further information. No responsibility is taken by either Castrol NZ, BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol New Zealand Limited  
Technical Advice Line 0800 10 40 60 Customer Service 0800 CASTROL (227 876)  
www.castrol.co.nz www.msds.castrol.co.nz