



Product Data

Duratec G

Proven robust performance with various gas types.

Description

Castrol Duratec G is a low ash SAE 40 engine oil, manufactured with high quality base stocks, designed for use in stationary gas engines operating on both sweet and sour natural gas, or landfill gas.

Application

Stationary gas engines are susceptible to many types of engine deposits and contamination, relating to the type of gas burned.

Deposits and contamination can reduce engine clearances, cause abrasive wear and contribute to increased oil consumption. This may necessitate more frequent maintenance downtime and higher running costs.

Castrol Duratec G can protect and extend the life of critical combustion chamber components against silicon-based deposits in landfill gas engines.

Castrol Duratec G also protects against piston deposits.

Approval Status

Castrol Duratec G is approved for use by several OEMs after demonstrating required performance in required field testing;

- Caterpillar
- Waukesha
- Rolls Royce
- Wartsila*

*awaiting formal letter of approval

Advantages

Castrol Duratec G provides the potential for extended drain intervals, lower oil consumption and protection against valve deposits.

After testing with natural and landfill gases in different OEM engines, Castrol Duratec G demonstrated:

- Excellent deposit and contamination control, ensuring engine clearances and cleanliness is maintained.
- Good engine wear protection.
- Low oil consumption.
- Optimised TBN retention to neutralise harmful acids and protect critical engine components.
- Resistance to damaging oxidation and nitration, avoiding premature oil degradation.

Typical Characteristics

Name	Method	Units	Typical Values
Relative Density @ 15°C	ASTM D4052	g/ml	0.87
Appearance	Visual	-	Clear & Bright
Colour	ASTM D1500	-	2
Kinematic Viscosity, Kinematic 100°C	ASTM D445	mm ² /s	13
Kinematic Viscosity, Kinematic 40°C	ASTM D445	mm ² /s	115.7
Viscosity Index	ASTM D2270	None	107
Total Base Number	ASTM D2896	mg KOH/g	5.8
Flash Point, PMCC	ASTM D93	°C	228
Flash Point, COC	ASTM D92	°C	274
Pour Point	ASTM D97	°C	-30
ASTM Noack Volatility	ASTM D5800	% wt	2.0
Sulphated Ash	ASTM D874	% wt	0.5
Phosphorus	ASTM D4951	% wt	250

The above figures are typical of those obtained with normal production tolerance and do not constitute a specification.

Storage

All packages should be stored under cover. Where outside storage is unavoidable drums should be laid horizontally to avoid the possible ingress of water and the obliteration of drum markings. Products should not be stored above 60°C, exposed to sunlight or freezing conditions.

Duratec G
19 Jan 2024

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

The Technology Centre, Whitchurch Hill, Pangbourne, Reading, RG8 7QR, United Kingdom
+44 (0)203 915 7991
www.castrol.com/globalbusiness