



INDUSTRIAL
LUBRICANTS &
SERVICES LIMITED

Technical Data sheet

ILS TF Fluid Regen (Uninhibited - Type I)

Severely Hydrotreated Naphthenic Electrical Insulating Oil

Description

ILS TF Fluid Regen (Uninhibited) is a high quality severely hydrotreated Naphthenic oil based Dielectric fluid produced from recovered Transformer Oil to meet IEC 60296 specifications. Designed for use as an insulating and cooling oil to fill air gaps, dissipate heat and insulate windings.

Typical Applications

ILS TF Fluid Regen (Uninhibited) is suitable for use in:

- Transformers
- Electrical switchgear
- Circuit breakers
- Capacitors

Advantages

- High dielectric strength and low power-loss
- Excellent Oxidation Stability
 - Low Dielectric Dissipation Factor
- Excellent cooling properties
- Good thermal stability
- High purity and high flash point
- Low sludge formation

Product Specifications

ILS TF Fluid Regen (Uninhibited) meets the specification requirements of:

- IEC 60296 ed.5, 2020, general requirements and special applications, including full declaration of additives per Clause 6.11.1
- BS 148:2009
- AS 1767
- TP PS 54 01 Issue 7 – Type B
- Corrosive Sulfur tests: ASTM D1275, DIN 51353 and IEC 62535

Typical Properties

	UNIT	METHOD	TYPICAL	MIN	MAX	
Density @ 20°C	g/ml	ISO 12185	0.881	-	0.895	
Closed Flash point (PMCC)	°C	ISO 2719	150	145	-	
Kinematic Viscosity @ 40°C	cSt	ISO 3104	10.15	-	12	
Kinematic Viscosity @ 100°C	cSt	ISO 3104	2.6	-	3	
Pour Point	°C	ISO 3016	-49	-	-40	
Acidity	mg	IEC 62021-1	< 0.01	-	0.01	
Water Content	KOH/g					
Bulk Delivery	ppm	IEC 6018148	< 10	-	30	
Drum Delivery	ppm	IEC 6018148	< 20	-	40	
Oxidation Stability						
Uninhibited (164 hr)	- Sludge	% mass	IEC 61125 C	0.25	-	0.8
	- Acidity	mgKOH/g	IEC 61125 C	0.65	-	1.2
Breakdown Voltage						
- Batch Result	kV/CM	IEC 60156	70	30	-	
- Delivered result	kV/CM	IEC 60156	> 70	30	-	
Dielectric dissipation factor (DDF)						
- @ 20°C - 50HZ	-	IEC 60156	0.0002	-	-	
- @ 90°C - 50HZ	-	IEC 60156	0.0004	-	0.005	
Resistivity						
- @ 20°C	G ohm m	BS 5737	15490	-	-	
- @ 90°C	G ohm m	BS 5737	800	-	-	
Interfacial tension @ 25°C	dyne/cm	ISO 6295	45	-	-	
Corrosive Sulphur	-	DIN 51353	Non corrosive	-	Non corrosive	
Potentially Corrosive Sulphur	-	-	Non corrosive	-	-	
DBDS	-	IEC 62697-1	< 5mg/Kg	-	< 5mg/Kg	
Antioxidant Content (Only DBPC)	% w/w	IEC 60666	< 0.01%	Not Detectable	0.01	
Appearance	-	-	clear & bright	-	-	
Carbon Type						
- Cn	-	-	46.0	-	-	
- Cp	-	-	44.0	-	-	
- Ca	-	-	10.0	-	-	
Total PCB content	g/g	IEC 61619	Not detectable	-	< 2	
Total Furans	g/g	IEC 61198	< 1	-	< 1	
Polycyclic Aromatics	% mass	IP 345	< 3	-	< 3	
As per IEC 60296 Ed5:2020 Article 5.4D, this product contains no undeclared additive						

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. See www.ils.co.nz No responsibility is taken by either ILS LTD for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.