

SURTAC® 2000 MULTISERVICE LUBRICANT

Whitmore's Surtac® 2000 is a "multiservice" lubricant for use on Draglines. Surtac® 2000 forms a protective coating on metal without the use of asphalt, solvents or lead.

Surtac® 2000 has won the confidence of both end users and OEMs. It has a well-established record on some of the most highly loaded and expensive open gear applications.

Surtac® 2000 contains graphite and MoS₂ (molybdenum disulfide). With the help of some specialized chemistry these solid lubricants bond with the metal surface. They form a dense gray-colored film, which minimizes metal-to-metal contact and wear. Using Surtac® 2000, lubricant consumption is reduced by about 50% compared to asphaltic fluids.

Many slow moving bearings and bushings can benefit from the use of Surtac® 2000, allowing lubricant inventories to be reduced.

Here are some hints for creating a protective coating with Surtac® 2000:

1. Do not contaminate with bearing grease or incompatible open gear lubricants.
2. Typical setting for open gears: Injectors at 50% open, and timed to lubricate every 30 minutes.
3. Avoid over lubrication.

Your Whitmore Distributor can work with you to minimize consumption, with maximum component protection.

Surtac® 2000 aerosol: Store aerosol cans at room temperature. Shake well before spraying.

BENEFITS:

- **LOWERS OPERATING TEMPERATURES** - extends gear life, reduces operating expenses.
- **MULTISERVICE LUBRICANT** - may be used on open gears, many bearings, bushings and some enclosed gears. Does not damage seals or packing materials used in pumping systems and injectors.
- **PUMPABILITY** - in many climates, a single grade can be used year-round. Consult Whitmore or Whitmore Distributor in selecting a suitable grade.
- **HIGH TEMPERATURE STABILITY** – the non-melt bentonite thickener ensures good performance on high-temperature gears, for example Kiln open gears.

APPLICATIONS:

Surtac® 2000 series is ideal for exposed parts on mining equipment such as swing racks, house rails and rollers, wire ropes, and drum laggings. It is suitable for many heavily loaded bushings including bushings on pneumatic hammers. Can be used in large heavily loaded bearings operating at or below a speed factor of 150,000 DN.

Additionally, Surtac® 2000 series can be used in some enclosed gear cases where the lubricant is not filtered or circulated by a pump. (Please consult Whitmore's Technical Service Dept. prior to using Surtac® 2000 in bearings or enclosed gear cases.) Surtac® 2000 grade is suitable for use on sealed pins and bushings of crawler tracks.

ASTM #		TYPICAL CHARACTERISTICS			
	Product Grade	Surtac® 2000	Surtac® 2000 RD	Surtac® 2000 HD	Surtac® 2000 XD
	Appearance	Heavy bodied oil	Very fluid grease	Soft grease	Grease
Gardner Method	Density , lb/gal @ 60°F (15.5°C) Specific Gravity , g/cc @ 60°F (15.5°C)	8.29 0.995	8.30 0.997	8.30 0.997	8.40 1.009
D-92	Flash Point , °F (°C) Cleveland Open Cup (Base Oils)	>230 (>110)	>230 (>110)	>230 (>110)	>230 (>110)
D-2596	Four Ball EP , Weld Point, kg	620	620	620	800
D-4048 Modified	Copper Strip Corrosion 212°F (100°C) @ 3 hr	1B	1B	1B	1B
OEM Standard	Low Temperature Pumpability Lincoln Ventmeter @ 400 psi, °F (°C)	-30 (-34)	-20 (-29)	15 (-9)	35 (2)

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.

PACKAGING

Shuttle Tanks	Drums	Kegs	Pails	Aerosol Cans 12 per case	Cartridges 50 per case	Caulking Tubes 24 per
---------------	-------	------	-------	-----------------------------	---------------------------	--------------------------

For warranty information, scan the QR code.
You can also email us at sales@whitmores.com
Or write to the Sales Department at the address below.

930 Whitmore Drive • Rockwall, Texas 75087 • USA • (972) 771-1000 • 800-699-6318
An ISO 9001 and ISO 14001 registered company • www.whitmores.com

